



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 505 022 A1

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **92300144.0**

(51) Int. Cl.⁵: **C01G 23/053**

(22) Date of filing: **08.01.92**

(30) Priority: **21.03.91 GB 9105980**

(43) Date of publication of application:
23.09.92 Bulletin 92/39

(84) Designated Contracting States:
BE DE ES FR IT NL SE

(71) Applicant: **TIOXIDE GROUP SERVICES LIMITED**
Tioxide House, 137-143 Hammersmith Road
London W14 0QL(GB)

(72) Inventor: **Jones, William John**
5 Vernon Place
Burnle, Tasmania 7320(AU)
Inventor: **Tooze, Judith Frances**
1 Blairmore Gardens, Eaglescliffe
Stockton on Tees, Cleveland TS16 9HX(GB)

(74) Representative: **Wilkinson, John**
Patent Department Central Laboratories
Portrack Lane
Stockton on Tees Cleveland(GB)

(54) **Method for preparing pigments.**

(57) A method for preparing pigmentary titanium dioxide is claimed. An aqueous solution of a titanium halide is mixed with 0.1 to 1.0% by weight titanium dioxide nuclei and the resultant mixture is heated in a sealed vessel to 150 to 300°C at which temperature it is maintained for at least 15 minutes. The mixture is subjected to ultrasonic vibrations for at least a part of the heating process.

The product of the process is useful as a white pigment without need for further treatment to optimise its particle size.

EP 0 505 022 A1

This invention relates to a method for preparing pigments and in particular to a method for preparing titanium dioxide pigments by hydrothermal precipitation.

Pigment grade titanium dioxide is commercially prepared generally by the so-called sulphate process or the so-called chloride process.

5 In the sulphate process a titanium-bearing ore such as ilmenite is reacted with sulphuric acid and the cake formed is dissolved in water or weak acid. The resultant solution after reduction and clarification is hydrolysed to precipitate hydrous titanium dioxide. After separation and washing the hydrous titanium dioxide is calcined to develop the crystal form and particle size distribution which is desirable for pigmentary titanium dioxide.

10 In the chloride process a titanium-bearing ore (e.g. rutile) is reacted with chlorine to form titanium tetrachloride which is then purified. The purified titanium tetrachloride is then reacted with oxygen at high temperatures to form pigmentary titanium dioxide.

The calcination step of the sulphate process and the oxidation step of the chloride process are both difficult to control to produce optimum pigmentary titanium dioxide and both require the input of large amounts of energy.

Alternative processes for the production of pigmentary titanium dioxide include autothermal processes in which an aqueous solution of a titanium compound is hydrolysed under the pressure generated by heating the solution above its boiling point in a sealed vessel. Generally, however, the particle size and particle size distribution of titanium dioxide produced by these methods are such that its pigmentary properties are poor.

The method of the present invention provides a titanium dioxide with good pigmentary properties.

According to the invention a method for preparing pigmentary titanium dioxide comprises mixing an aqueous solution of a titanium halide with an amount of particulate titanium dioxide nuclei comprising 0.1 to 1.0% by weight based on weight of titanium halide expressed as TiO_2 , heating the mixture so obtained over a period in a sealed vessel to a temperature of from 150°C to 300°C and maintaining the mixture at a temperature between 150°C and 300°C for a further period of at least 15 minutes wherein the said mixture is subjected to the effect of ultrasonic vibrations during at least a part of at least one of said periods.

The titanium halide which is converted to titanium dioxide by the method of the invention can be any titanium halide which can be dissolved in water but which hydrolyses when heated under the conditions of the method. The most useful titanium halides are titanium chlorides.

The titanium halide is used in the method of the invention in the form of an aqueous solution. When a titanium chloride is employed the solution is, for example, prepared by diluting substantially pure titanium tetrachloride with water or by digesting ilmenite in hydrochloric acid.

The concentration of the aqueous solution is such that it, preferably, contains an amount of titanium
35 halide equivalent to from about 50g/l to about 300 g/l titanium dioxide.

The particles of titanium dioxide which are used as nuclei have a particle size which promotes the formation of pigmentary titanium dioxide which is the product of the method of the invention.

The nuclei can be formed by any suitable process but, typically, a portion of the aqueous solution of titanium halide is diluted with 5 to 10 times its own volume of water and the resultant solution is boiled for 40 about 15 minutes.

Nuclei can be so-called rutile nuclei or anatase nuclei i.e. they tend to promote formation of rutile titanium dioxide or anatase titanium dioxide during the formation of the titanium dioxide. The size of nuclei can be extremely difficult to measure but there have been indications that one form of rutile promoting nuclei, when dry, is acicular in shape having a size of the order of 12 nm to 17.5 nm by 5 nm to 9 nm. One form of anatase promoting nuclei is approximately spherical and has a particle diameter of from say 2.5 nm to 7 nm.

The amount of nuclei used, to some extent, determines the final crystal size of the pigmentary titanium dioxide formed and a nuclei concentration of 0.1 to 1.0% by weight based on weight of titanium halide expressed as TiO_2 is used. Preferably 0.3 to 0.6% by weight with respect to titanium halide expressed as TiO_2 is used.

The pigmentary titanium dioxide is formed by heating the aqueous solution and particulate titanium dioxide nuclei in a sealed vessel to a temperature between 150°C and 300°C and subsequently maintaining the mixture at a temperature within this range for at least 15 minutes. The mixture is preferably maintained at this elevated temperature for between 15 and 90 minutes and, more preferably, for between 15 and 30 minutes.

Most preferably, the mixture is heated to a temperature between 200°C and 250°C and held at a temperature in that range for at least 15 minutes.

During at least a part of at least one heating period the mixture is subjected to the effect of ultrasonic

te formation of rutile
de. The size of nuclei
m of rutile promoting
by 5 nm to 9 nm. One
er of from say 2.5 nm

e pigmentary titanium
ght of titanium halide
n halide expressed as

d particulate titanium
C and subsequently
e mixture is preferably
preferably, for between

250 ° C and held at a

the effect of ultrasonic

!!
}) kello
maä rää
mo do
← yn pin
maä rää
vanhahten
loppuista
kidekohta
Ei
maä rää
vanhahten
fotokattuvissa
~~toimittavissa~~
↓
Hilja Järvi
5.12.78
Ei. Omin mieltään
Ei pöytäkirjassa
Ei. Omin mieltään
Omin mieltään

vibrations. Preferably the ultrasonic vibrations are maintained throughout both the heating periods.

The ultrasonic vibrations used in the method of the invention are those known as power ultrasound usually employing frequencies of 10 kHz to 50 kHz but the preferable frequency is about 20 kHz. Preferably the ultrasonic power output into the mixture is within the range 100 to 500 watts per litre of mixture and most desirably within the range 250 to 350 watts per litre.

Any equipment which can withstand the autothermal pressures developed in the method can be used but a convenient apparatus for laboratory scale experiments consists of a substantially cylindrical autoclave equipped with an axially aligned ultrasonic horn which is arranged so as to be immersed in the mixture during the heating periods.

The product of the method of the invention is useful as a white pigment in, for example, paints, inks, paper and plastics without need for further treatment to optimise its particle size and particle size distribution. The pigmentary properties and, in particular, tinting strength are considerably better than for titanium dioxide prepared in a similar manner but without the use of ultrasonic vibrations.

The pigmentary titanium dioxide can be coated with inorganic or organic compounds by conventional techniques to further improve properties such as durability and dispersibility.

The invention is particularly described by the following examples.

Example 1

An aqueous solution of titanium chloride was formed by diluting titanium tetrachloride with sufficient water so as to contain the equivalent of 140 g/l TiO_2 . 550 mls of the solution were placed in an autoclave having a nominal capacity of 1 litre made from Hastelloy C-276 and having a tantalum liner. A slurry of titanium dioxide nuclei was prepared by diluting 2.5 mls of the aqueous titanium chloride solution with water in a ratio of 7.5 parts water to 1 part solution by volume and the diluted solution was boiled for 15 minutes. This slurry was added to the autoclave giving a concentration of nuclei of 0.5% with respect to Ti in solution. An ultrasonic horn was positioned so as to be immersed within the aqueous solution and the autoclave was sealed. Electric power was supplied to the ultrasonic horn whilst the mixture of aqueous solution and nuclei was heated to 200°C. The sound produced had a frequency of 20 kHz at a power of 200 watts. After holding the mixture for 30 minutes at 200°C the ultrasonic horn was switched off and the autoclave was allowed to cool to room temperature.

Titanium dioxide which had been formed was separated by filtration, washed with water and acetone and dried at room temperature. After grinding by hand, the tinting strength was found to be 1590.

Example 1A (Comparative)

Example 1 was repeated except that no electric power was supplied to the ultrasonic horn. After grinding the tinting strength of the titanium dioxide formed was found to be 1120.

Example 2

Example 1 was repeated except that the aqueous solution was heated to 250°C and held at this temperature for 30 minutes in the presence of 0.5% by weight of nuclei expressed as TiO_2 . After grinding the tinting strength of the titanium dioxide produced was found to be 1600.

A sample of the titanium dioxide produced was compared with a standard uncoated rutile titanium dioxide prepared by the chloride process in an air-drying resin sold under the name of Sobral P470 at 17% pigment volume concentration with the following results

	Contrast Ratio of 25 microns film	Scattering Coefficient (microns^{-1})
Example 2	92.0%	2.685
Standard	93.1%	2.618

Claims

1. A method for preparing pigmentary titanium dioxide characterised in that an aqueous solution of a titanium halide is mixed with an amount of particulate titanium dioxide nuclei comprising 0.1 to 1.0% by weight based on weight of titanium halide expressed as TiO_2 , the mixture so obtained is heated over a

period in a sealed vessel to a temperature of from 150 °C to 300 °C and the mixture is maintained at a temperature between 150 °C and 300 °C for a further period of at least 15 minutes the said mixture being subjected to the effect of ultrasonic vibrations during at least a part of at least one of said periods.

5

2. A method according to claim 1 characterised in that the titanium halide is a titanium chloride.

3. A method according to claim 2 characterised in that the aqueous solution of titanium chloride is prepared by diluting substantially pure titanium tetrachloride with water.

10

4. A method according to claim 2 characterised in that the aqueous solution of titanium chloride is prepared by dissolving ilmenite in hydrochloric acid.

15

5. A method according to any one of the preceding claims characterised in that the aqueous solution of titanium halide has a concentration equivalent to from about 50 g/l to about 300 g/l titanium dioxide.

20

6. A method according to any one of the preceding claims characterised in that the particulate titanium dioxide nuclei are prepared by diluting a portion of the aqueous solution of titanium halide with water in a ratio of 5 to 10 volume parts of water to 1 volume part of aqueous solution and boiling the diluted solution produced for about 15 minutes.

25

7. A method according to any one of the preceding claims characterised in that the nuclei are acicular in shape and have a longest dimension of from 12 nm to 17.5 nm and a shortest dimension of from 5 nm to 9 nm.

8. A method according to any one of claims 1 to 6 characterised in that the nuclei are approximately spherical and have a particle diameter of from 2.5 nm to 7 nm.

30

9. A method according to any one of the preceding claims characterised in that the amount of particulate titanium dioxide nuclei used is from 0.3 to 0.6% by weight with respect to titanium halide expressed as TiO₂.

35

10. A method according to any one of the preceding claims characterised in that the mixture is heated at a temperature between 150 °C and 300 °C for a period of between 15 and 90 minutes.

11. A method according to any one of the preceding claims characterised in that the mixture is heated to a temperature between 200 °C and 250 °C and is held at a temperature between 200 °C and 250 °C for at least 15 minutes.

40

12. A method according to any one of the preceding claims characterised in that the ultrasonic vibrations employed have a frequency of from 10 kHz to 50 kHz.

13. A method according to any one of the preceding claims characterised in that the ultrasonic vibrations employed have a power output into the mixture of from 100 to 500 watts per litre of mixture.

45

14. An apparatus suitable for carrying out the method of any one of the preceding claims comprising a substantially cylindrical autoclave characterised in that an axially aligned ultrasonic horn is arranged so as to be immersed in the liquid during the heating period.

50

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 92 30 0144

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
A	GB-A-1 109 838 (DOW CHEMICAL CO.) * the whole document * ---	1, 2, 7, 10, 11	C01G23/053
A	DE-A-1 467 319 (DOW CHEMICAL CO.) * the whole document * ---	1, 2, 4, 5, 6, 7	
A	WORLD PATENTS INDEX LATEST Derwent Publications Ltd., London, GB; AN 82-80724E & SU-A-882 932 (DOBROVOLSKII) * abstract * ---	1, 13	
A	PATENT ABSTRACTS OF JAPAN & JP-A-60 226 413 (KOGYO GIJUTSUIN) * abstract * ---	1, 12, 13	
A	US-A-3 528 773 (J. P. SURLS) ---		
A	US-A-3 329 484 (R. S. LONG) ---		TECHNICAL FIELDS SEARCHED (Int. Cl.5)
A	US-A-3 635 671 (E. C. TVETER) -----		C01G
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 29 JUNE 1992	Examiner e. libbrecht-verbeeck
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone V : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			
T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document			